


Telefon: +49 (0)4171 / 8480-0 Homepage: www.ampri.de e-mail: info@ampri.de

Technical Data Sheet

4MPri

Article-No.: **191-012**Description: **Black 300**

Nitrile examination glove black, non sterile, powder free





PRODUCT DESCRIP	IION						
material	Latex	✓ Nitrile	Vinyl	☐ Vinyl-Nitrile-	Polyethy-lene	☐ TPE	cotton
	I		✓ black	mixture	(PE)		
colour	□ white	□ blue		□ mint	□ purple	□ mix	apple-green
characteristics	prepowdered	✓ powderfree	sterile	✓ non sterile		fits hand- specific	☐ biodgra- dable
surface	☐ full textured	finger textured	☐ not textured	☐ embossed	☑ chlorinated ins	iide	
SIZES							
	XS (5-6)	S (6-7)	M (7-8)	L (8-9)	XL (9-10)	XXL (10-11)	XXXL (11-12)
width	≤ 80 mm	80 ± 10 mm	95 ± 10 mm	110 ± 10 mm	115 ± 10 mm	-	-
length	≥ 300 mm	≥ 300 mm	≥ 300 mm	≥ 300 mm	≥ 300 mm	-	-
REGULATORY AFFA	IDC						
PPE-Regulation (EU) 2016/425	☐ Category I	☐ Category II	☑ Category III	☐ no PPE-article			((
MD-Regulation (EU) 2017/745	☑ Class I	Class II a	Class III	sterile	measuring function	no medical device	CE
Food Contact (EG) 1935/2004	☑ acidic foods	aqueous food	☑ fatty foods	alcoholic foods	dry foods	not approved for food-contact	5217
STANDARDISATION							
EN 388 Mechanical	abrasion	blade cut	tear resistance	puncture	blade cut	impact test	
Risks	resistance	resistance Coupe-Test		resistance	resistance TDM-Test		
Level	not applicable						
EN 374-1	chemical		code letter	level	permeation time	degradation	
Chemical Risks	Sodium hydroxide	40%	K	6	> 480 min	15,1 %	ISO 374-1/Type B
Circinical Risks	Hydrogen Peroxide		Р	2	> 30 min	-74,4 %	
EN 374-4	Formaldehyde 37%		Т	5	> 240 min	24,0 %	
Degradation	, , , , , , , , , , , , , , , , , , , ,			-	-	,	
Degradation							
							KPT
EN 374-5 microorganism tightness	The glove is tight against microorganisms (viral, bacteria and fungi). Test according to ISO 16604 - method B.					EN ISO 374-5:2016 VIRUS	
EN ISO 21420 protective gloves	The glove meets the requirements according to EN ISO 21420						
EN 455 medical gloves for single use	The glove meets the requirements according to EN 455-1, EN 455-2, EN 455-3, EN 455-4					EN 455	
EN 455-1 freedom from holes	The glove has an AQL < 1.5 in regards to the water retention test (sampling inspection in acc. to ISO 2859-1, general Inspection Level I)					AQL 1.5	
ISO 18889 Pesticide application	not applicable						



21423 Winsen (Luhe) - Germany Telefon: +49 (0)4171 / 8480-0 Homepage: www.ampri.de e-mail: info@ampri.de

Technical Data Sheet

Article-No.: **191-012**Description: **Black 300**


Nitrile examination glove black, non sterile, powder free

LOGISTIC DATA	SUBPACKING		
generell informati	on		
material	carton		
pieces per subpacl	king	100	
GTIN subpacking s	ize XS	4044941730073	
GTIN subpacking s	ize S	4044941730097	
GTIN subpacking s	4044941730110		
GTIN subpacking s	4044941730134		
GTIN subpacking s	4044941730158		
GTIN subpacking s	ize XXL	-	
GTIN subpacking s	-		
PZN subpacking siz	=		
PZN subpacking siz	te S	-	
PZN subpacking siz	-		
PZN subpacking siz	e L	-	
PZN subpacking siz	-		
PZN subpacking siz	-		
PZN subpacking siz	-		
measures & size			
length		280 mm	
width	135 mm		
heigth		60 mm	
weights			
size	net weight	gross weight	
XS	440 g	500 g	
S	480 g	540 g	
M	520 g	580 g	
L	560 g	620 g	
XL	620 g	680 g	
XXL	-	-	
XXXL	-	-	

LOGISTIC DATA	PALETTE	
general information	n	
kind of palett		euro-palette
measures & size		
cartons per layer	8	
layers per palette		6
heigth of the palette	e	195 cm
weights		
size	net weight	gross weight
XS	264 g	289 g
S	283 g	308 g
M	302 g	327 g
L	322 g	347 g
XL	350 g	375 g
XXL	-	-
XXXL	_	-



LOGISTIC DATA	OUTER PACKING		
generell informatio			
material		carton	
subpackings per out	er packing	10	
GTIN outer packing size XS		4044941730080	
GTIN outer packing	4044941730103		
GTIN outer packing	4044941730127		
GTIN outer packing	size L	4044941730141	
GTIN outer packing	4044941730165		
GTIN outer packing	-		
GTIN outer packing	size XXXL	-	
PZN outer packing s	ize XS	-	
PZN outer packing s	ize S	-	
PZN outer packing s	ize M	-	
PZN outer packing s	-		
PZN outer packing s	-		
PZN outer packing s	-		
PZN outer packing s	-		
measures & size			
length	310 mm		
width	290 mm		
heigth		300 mm	
weights			
size	net weight	gross weight	
XS	5.000 g	5.500 g	
S	5.400 g	5.900 g	
М	5.800 g	6.300 g	
L	6.200 g	6.700 g	
XL	6.800 g	7.300 g	
XXL	-	-	
XXXL	-	-	





21423 Winsen (Luhe) - Germany Telefon: +49 (0)4171 / 8480-0

Homepage: www.ampri.de e-mail: info@ampri.de

Technical Data Sheet

Article-No.: **191-012**Description: **Black 300**

Nitrile examination glove black, non sterile, powder free



WARNINGS AND SAFETY INFORMATION

storage /	expi	iry
date		

Store gloves in original packaging in a cool and dry place without additional weight, protect from direct sunlight. Do not store near ozone sources (laser printers, copiers). The actual expiry time in use cannot be specified in general terms, as it depends on the general conditions of use. An individual risk assessment must be carried out in each case. The expiry date - valid for proper storage - is stated on the packaging.

use and control

Always use protective gloves only for the intended use and in the correct size. A check/risk assessment must be carried out to ensure that the gloves are suitable for the intended use, as the conditions at the workplace may deviate from those of the type test depending on temperature, abrasion and degradation. Breakthrough times and permeation levels are based on laboratory measurements and are determined using samples taken from the palm of the hand. The actual duration of protection of a glove with a specific substance can vary significantly due to the conditions of use (temperature, abrasion, stretching). In the case of aggressive chemicals, degradation (change in mechanical properties) can be an important factor to consider when selecting chemical-resistant gloves. This information does not reflect the actual duration of protection in the workplace and the distinction between mixtures and pure chemicals. The chemical resistance was determined under laboratory conditions only on the basis of samples from the palm and refers only to the chemicals tested. The situation may be different if the chemical is used in a mixture. The penetration resistance was evaluated under laboratory conditions and refers only to the tested specimen. The degradation results according to EN ISO 374-4 show the change in puncture resistance of the gloves after exposure to the tested chemical.

Before use, the gloves must be checked for holes or damage.

disposal

Used gloves must be disposed of after contact with chemicals in accordance with the disposal regulations for the chemical and the regulations of the local waste disposal company. Unused gloves can be disposed of with household waste.

disinfection

Disinfection is not intended for these gloves and is the responsibility of the user.

warnings/ allergy information

Protective gloves are intended for single use only.

This product contains dithiocarbamates, which may cause allergic reactions

donning and doffing instructions











rev-no.:

date 03. 09.2024

changes and errors excepted